





Pipe Size (inches)	Outside Diameter (inches)	Identification			Wall Thickness--t- (inches)	Wt/Ft Pounds	Pipe Size (inches)	Outside Diameter (inches)	Identification			Wall Thickness -t- (inches)	Wt/Ft Pounds	
		Steel		Stainless Steel Schedule					Steel		Stainless Steel Schedule			
		Iron Pipe Size	Schedule No.						Iron Pipe Size	Schedule No.				
14	14.00	.	.	5S	.156	23.07	16	16.00	.	.	5S	.165	27.90	
		.	.	10S	.188	27.73			.	.	10S	.188	31.75	
		.	10	.	.250	36.71			.	10	.	.250	42.05	
		.	20	.	.312	45.61			.	20	.	.312	52.27	
		STD	30	.	.375	54.57			.	30	.	.375	62.58	
		.	40	.	.438	63.44			STD	40	.	.500	82.77	
		XS	.	.	.500	72.09			XS	60	.	.656	107.50	
		.	60	.	.594	85.05			.	80	.	.844	136.61	
		.	80	.	.750	106.13			.	100	.	1.031	164.82	
		.	100	.	.938	130.85			.	120	.	1.219	192.43	
		.	120	.	1.094	150.93			.	140	.	1.438	223.64	
		.	140	.	1.250	170.21			.	160	.	1.594	245.25	
		.	160	.	1.406	189.11								
18	18.00	.	.	5S	.165	31.43	20	20.0	.	.	5S	.188	39.78	
		.	.	10S	.188	35.76			.	.	10S	.218	46.06	
		.	10	.	.250	47.39			.	10	.	.250	52.73	
		.	20	.	.312	58.94			.	20	.	.375	78.60	
		STD	.	.	.375	70.59			STD	30	.	.500	104.13	
		.	30	.	.438	82.15			XS	40	.	.594	123.11	
		XS	.	.	.500	93.45			.	60	.	.812	166.40	
		.	40	.	.562	104.67			.	80	.	1.031	208.87	
		.	60	.	.750	138.17			.	100	.	1.281	256.10	
		.	80	.	.938	170.92			.	120	.	1.500	296.37	
		.	100	.	1.156	207.96			.	140	.	1.750	341.09	
		.	120	.	1.375	244.14			.	160	.	1.969	379.17	
		.	140	.	1.562	274.22								
.	160	.	1.781	308.50										
22	22.00	.	.	5S	.188	43.80	24	24.00	.	.	5S	.218	55.37	
		.	.	10S	.218	50.71			.	10	10S	.250	63.41	
		.	10	.	.250	58.07			STD	20	.	.375	94.62	
		STD	20	.	.375	86.61			XS	.	.	.500	125.49	
		XS	30	.	.500	114.81			.	30	.	.562	140.68	
		.	60	.	.875	197.41			.	40	.	.688	171.29	
		.	80	.	1.125	250.81			.	60	.	.969	238.35	
		.	100	.	1.375	302.88			.	80	.	1.219	296.58	
		.	120	.	1.625	353.61			.	100	.	1.531	367.39	
		.	140	.	1.875	403.00			.	120	.	1.812	429.39	
		.	160	.	2.125	451.06			.	140	.	2.062	483.12	
		.		.					.	160	.	2.344	542.13	
		26	26.00	.	10	.			.312	85.60	28	28.00	.	10
STD	.			.	.375	102.63	STD	.	.	.375			110.64	
XS	20			.	.500	136.17	XS	20	.	.500			146.85	
30	30.00	.	.	5S	.250	79.43	32	32.00	.	10	.	.312	105.59	
		.	10	10S	.312	98.93			.	20	.	.375	126.66	
		STD	.	.	.375	118.65			STD	.	.	.500	168.21	
		XS	20	.	.500	157.53			XS	30	.	.625	209.43	
34	34.00	.	10	.	.312	112.25	36	36.00	.	5S	.	.250	95.54	
		STD	.	.	.375	134.67			.	10	.	.312	118.92	
		XS	20	.	.500	178.89			.	20	.	.375	142.68	
		.	30	.	.625	222.78			STD	.	.	.500	189.57	
42	42.00	STD	.	.	.375	166.71	48	48.00	STD	40S	.	.375	190.74	
		XS	20	.	.500	221.61			.	.	.	.500	253.65	
		.	30	.	.625	276.18								
		.	40	.	.750	330.41								



Premier Materials, Inc.
9705 Port Erroll Rd.
Houston TX 77095
Ph: 281-463-3036 Fax: 281-463-3036



WEIGHT FORMULA WT/FT=10.69X(OD-WALL THICKNESS) X WALL THICKNESS